


PREN

Pitting Resistance Equivalent Number



The higher the PREN-value (pitting resistance equivalent number), the more resistant is the alloy to localized pitting corrosion by aqueous salt solution. $PREN = Cr + 3.3Mo + 16N$

AL-6XN® is a registered trademark of ATI Properties, Inc.

Ultra 6XN® is a registered trademark of Outokumpu.